

*included*

contained coagulated matters of the polymer fine particles. When a film is produced by forming into the film from the polyolefin-based composition, there were problems that the coagulated matters are not dispersed, white spots caused by the coagulated matters are generated, the appearance of the film is deteriorated, and points not inked to the film are generated at printing, etc.--

Please replace Table 2 on page 24, with the following amended

Table 2:

-- Table 2 Physical properties of film

*B2*

	Amount of polymer fine particle added	Haze	LSI	Anti- blocking property	Numbers of white spot (size 0.2 to 1mm)
	% by weight			MPa (kg/12cm <sup>2</sup> )	Pieces/ 25cm <sup>2</sup>
Example 1	0.3	3.1	2.3	0.71 (0.6)	8
Example 2	0.3	3.0	2.4	0.71 (0.6)	6
Example 3	0.3	3.0	2.3	0.59 (0.5)	8
Example 4	0.3	2.4	2.7	0.71 (0.6)	6
Comparative Example 1	0.3	3.3	2.6	0.71 (0.6)	80

--